



larger image

Results 1 - 19 of 19

1

Item #	Item Name	Ratio	Viscosity	Work Life	Shear Strength	Dielectric Strength	Temperature Resistance	MSDS	TDS
MP 5405	MP 5400 Series Maximum Performance Epoxies	1 to 1	12500 cps	3 min. - 5 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 5405BK	MP 5400 Series Maximum Performance Epoxies	1 to 1	13000 cps	3 min. - 5 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 5405NS	MP 5400 Series Maximum Performance Epoxies	1 to 1	90000 cps	3 min. - 5 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 5405Flex	MP 5400 Series Maximum Performance Epoxies	1 to 1	9500 cps	3 min. - 5 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 5430	MP 5400 Series Maximum Performance Epoxies	1 to 1	13000 cps	20 min. - 30 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54110	MP 5400 Series Maximum Performance Epoxies	1 to 1	45000 cps	9 min. - 12 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54110GR	MP 5400 Series Maximum Performance Epoxies	1 to 1	45000 cps	9 min. - 12 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54125	MP 5400 Series Maximum Performance Epoxies	1 to 1	48000 cps	25 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54125GR	MP 5400 Series Maximum Performance Epoxies	1 to 1	47000 cps	25 min.	2000 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54190	MP 5400 Series Maximum Performance Epoxies	1 to 1	15000 cps	70 min. - 100 min.	3300 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54190GR	MP 5400 Series Maximum Performance Epoxies	1 to 1	60000 cps	70 min. - 100 min.	3300 - 4000 psi	400 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54270	MP 5400 Series Maximum Performance Epoxies	1 to 1	20000 cps	60 min.	1800 - 3000 psi	550 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54270BK	MP 5400 Series Maximum Performance Epoxies	1 to 1	20000 cps	60 min.	1800 - 3000 psi	550 Volts/mils.	-60°F to 250°F	MSDS	TDS
MP 54420	MP 5400 Series Maximum Performance Epoxies	2 to 1	43000 cps	20 min. - 30 min.	4000 - 5000 psi	500 Volts/mils.	-60°F to 300°F	MSDS	TDS
MP	MP 5400 Series Maximum Performance Epoxies	2 to 1	40000 cps	50 min.	4000 - 5000 psi	500 Volts/mils.	-60°F to 250°F	MSDS	TDS